

ARCTEC® 308L FLUX CORED

Conforms to: AWS A5.22-95 E308LT1-1/T1-4
ASME SFA5.22
CWB to AWS A5.22-95 E308LT1-1/T1-4



a quality welding alloy

GENERAL CHARACTERISTICS:

ARCTEC® 308L FLUX CORED is an all position flux cored wire for welding stainless steels with shielding gas. This wire has a fast freezing slag system, which facilitate out of position welding. The low carbon content increases resistance to intergranular corrosion without the addition of stabilizers such as columbium or titanium. It performs equally well when welding out of position and flat and horizontal.

APPLICATIONS:

ARCTEC® 308L FLUX CORED is designed for joining and cladding of types 301, 302, 304, 304L and 308L austenitic stainless steels. May be used for welding type 321 and 347 where service the temperature does not exceed 500° F (260° C)

MECHANICAL PROPERTIES:

Tensile Strength	Elongation	ft-lbs	Impact Value Joule	Temperature
85,600psi(590Mpa)	40%-2"	52	70	-4° F (-20°C)

OPERATING PARAMETERS:

WELDING PROCESS: FCAW POLARITY: DC Reverse SHIELDING GAS: 100% CO₂ or 75% Argon /25% CO₂

Welding Parameters			
Diameter	Position	Amps	Volts
.035"	Flat	130-170	27-32
.035"	Horizontal	130-170	25-30
.035"	Vertical up	100-140	25-30
.035"	Overhead	100-140	25-30
.045"	Flat	140-180	25-30
.045"	Horizontal	140-180	25-30
.045"	Vertical up	100-140	25-30
.045"	Overhead	100-140	25-30
1/16"	Flat	250-290	28-33
1/16"	Horizontal	250-290	25-30

STANDARD SIZE AND PACKAGING:

Size	Packaging
.045" (1.2mm) 1/16" (1.5mm)	12" spools (15 Kg)

CALGARY FAX:(403)-250-7682 EDMONTON: (780)-484-4896 VANCOUVER: (604)-596-2940 WINNIPEG: (204)-663-7955
PHONE:(403)-250-9355 (780)-484-3304 (604)-596-6207 (204)-663-9182

The seller makes no warranties, express or implied, including, but not limited to, the implied warranties of merchantability and fitness for a particular purpose, except as expressly stated in seller's contract, delivery slip or invoice form. Technical data and suggested application are provided to assist you in making your own evaluations and decisions and should not be interpreted as expressed or implied warranties. Mechanical properties are typical or average values obtained by testing and comparing many heats of the same alloys. Minimum and maximum values are noted accordingly and are not intended for specific purposes.

Subject to change without notice

OHO260905/284-1